

CuSn5

EN_2024_06

Comparable standards: UNS C51000 • EN CW451K • JIS C5102
 Aurubis designations: C510 • PNA 285

Description CuSn5 is a solid solution strengthened copper alloy with 5% tin (bronze). It combines very good cold workability with high strength and hardness. The alloy is corrosion resistant and can be well soldered and brazed, yet it still has good electrical conductivity. CuSn5 is used in applications where great importance is attached to the combination of conductivity and strength.

Composition

Cu	Sn	P	Pb	Zn
[%]	[%]	[%]	[%]	[%]
rem	4.5-5.5	0.01-0.4	0.02 max	0.2 max

Composition of this alloy is in accordance with RoHS for electric & electronic components and ELV for the automotive industry.

Physical properties

Melting point	Density	c _p @ 20°C	Young's modulus	Thermal cond.	Electrical cond.		α @20-300°C
					[°C]	[g/cm ³]	
1049	8.9	0.377	120	96	≥ 10	≥ 17	18

Note: The specified conductivity applies to the soft condition only.

c_p specific heat capacity
 α coefficient of thermal expansion

Mechanical properties

	Tensile Strength	Yield Strength	Elongation A ₅₀	Hardness HV	Bend ratio 90° [r]		Bend ratio 180° [r]	
					[MPa]	[MPa]	[%]	[-]
R310	310-390	≤ 250	≥ 45	75-105	0	0	0	0
R400	400-500	≥ 240	≥ 14	120-160	0	0	0	0
R490	490-580	≥ 430	≥ 8	160-190	0	0	1	2
R550	550-640	≥ 510	≥ 4	180-210	0	1.5	2	3
R630	630-720	≥ 600	≥ 2	200-230	1.5	4	3	5
R690	≥ 690	≥ 670	-	≥ 220	2.5	9	-	-

r = x * t (thickness t ≤ 0.5mm)
 GW bend axis transverse to rolling direction. BW bend axis parallel to rolling direction.

Fabrication properties

Cold formability	excellent
Hot formability	not recommended
Soldering	excellent
Brazing	excellent
Oxyacetylene welding	fair
Gas shielded arc welding	good
Resistance welding	good
Machinability	not recommended

Electrical conductivity	The electrical conductivity depends on chemical composition, the level of cold deformation and the grain size. A high level of deformation as well as a small grain size decrease the conductivity.
Corrosion Resistance	<p>Bronze is resistant to: Natural and industrial atmospheres as well as maritime air, drinking and service water (if the flow rate is not excessive), seawater, non oxidizing acids, alkaline solutions and neutral saline solutions.</p> <p>Bronze is not resistant to: Ammonia, halogenide, cyanide and hydrogen sulfide solutions and atmospheres, oxidizing acids.</p> <p>Bronze alloys have an improved resistivity towards seawater and pitting corrosion.</p>
Typical uses	Automotive, components of electrical engineering, connectors, relays and conductor springs, retaining clamps, springs, metal hose, bushings and mechanical and apparatus engineering.

This leaflet is for general information only and is not subject to revision. No claims can be derived from it unless there is evidence of intent or gross negligence. The data given are no warranty that the product is of a specified quality and they cannot replace expert advice or the customer's own test.